

# SIL-BOND RTV-6500 (Acetoxy)

## HIGH TEMPERATURE 1-PART INDUSTRIAL/CONSTRUCTION GRADE SILICONE SEALANT

Sil-Bond (RTV 6500) is a premium high temperature one component room temperature vulcanizing RTV acetoxy cure silicone sealant and adhesive. When fully cured, this unique VOC compliant formula offers tenacious adhesion to form waterproof and airtight bonds to materials in high temperature scenarios, such as: metal, steel, tile, ceramic, glass, aluminum, painted surfaces, marble and many other common substrates. This product is specifically formulated to offer all weather performance to meet today's Green Building Standards.

### FEATURES & BENEFITS

- High Temperature Performance
- Excellent Weatherability
- UV Stable
- Non-Yellowing
- VOC Compliant
- Non-Flammable
- Waterproof
- Excellent Adhesion
- Non-Shrinking

### CONSTRUCTION & INDUSTRIAL APPLICATIONS

Sealing & Glazing	Flues & Venting
HVAC/R	Transportation Seals
Plumbing	Appliance Trim
Roofing	Interior/Exterior
Kitchen & Bath	Above Grade
Furnace & Fireplace	

**MEETS SPECIFICATIONS:** ASTM C920 Type S, Grade NS, Class 25; TT-S-00230C (COM-NBS), TT-S-01543A (COM-NBS), MIL-A-46106A, FDA CFR 177.2600, USDA Approved, NSF 51, UL Recognized Component.

**AVAILABLE COLORS:** Red

### PHYSICAL PROPERTIES

### TEST METHOD

Cure System	Acetoxy	
Movement Capability, %	±25%	ASTM C-719
Modulus	Medium	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min.	370	ASTM C-1183
1/8" orifice @ 50 psi		Modified
Temperature Range	-62°F to 500°F	
Intermittent Temperature Range	650°F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	10*	MNA Method
Tack Over Time (min)	17*	ASTM C-679
Cure Rate	1/8" per 24hrs*	MNA Method
Tensile Strength (psi)	310	ASTM D-412
Elongation %	500	ASTM D-412
Durometer Shore A	26	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.9 @ 60	
Shelf Life (months)	24	
Volatile Organic Content	30 gr./liter	

\*All properties derived from lab conditions (77° F at 50% relative humidity)

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.



For orders or more information contact:  
 Caliber Supply, LLC Phone (480) 336-8342  
 Caliber-Supply.com